



Typical Physical Properties PLASTOLYN hydrocarbon resins

Some products contain physical properties that are not displayed in the columns below. To locate the information needed, please choose the product link below. The properties may be found on the datasheet, SDS or sales specification.

Plastolyn (Hydrogenated Hydrocarbon Resins)

Products	Ring and Ball Softening Point	Molecular Weight ^a				Data Sheet	SDS
	ASTM D 6493	M _n	M _w	M _w /M _n	M _z		
Plastolyn™ R1140	140 °C	900	1500	1.7	2400		

^a - Molecular weight measured via Gel Permeation Chromatography (GPC) using polystyrene standards

Plastolyn (Pure Monomer Resin)

Products	Ring and Ball Softening Point	Molecular Weight ^a				Data Sheet	SDS
		M _n	M _w	M _w /M _n	M _z		
Plastolyn™ 240	121 °C	1150	3800	4.0	8500		
Plastolyn™ 290	140 °C	1350	5200	3.3	14000		
Plastolyn™ 290LV	140 °C	1500	3700	2.5	7300		

^a - Molecular weight measured via Gel Permeation Chromatography (GPC) using polystyrene standards