

Eastman™ performance additives and polymers**Hydrocarbon resin additives (Typical properties)**

	Product	T _g °C	RBSP °C	Gardner color	M _z	M _w	M _n	P _d
Aromatic pure monomer resins	Kristalex™ F115	65	115	<1	3,300	2,000	1,200	1.7
	Kristalex™ 5140	85	139	<1	12,100	4,900	1,500	3.3
	Endex™ 160	105	159	<1	18,400	8,600	2,500	3.6
	Picolastic™ D125	64	126	2	179,000	37,400	1,300	28.5
	Plastolyn™ 290	84	140	<1	13,000	5,200	1,350	4.0
Aliphatic hydrogenated hydrocarbon resins	Regalrez™ 1126	67	124	<1	2,050	1,250	700	1.8
	Plastolyn™ R1140	91	140	<1	2,800	1,500	800	1.9
	Regalite™ R1125	70	123	<1	2,100	1,300	800	1.6
Mixed (aliphatic/aromatic) hydrogenated hydrocarbon resins	Regalite™ S5100	55	97	<1	1,800	900	600	1.5
	Regalrez™ 3102	51	102	<1	2,350	1,450	800	1.8
	Regalrez™ 6108	55	108	<1	2,300	1,400	750	1.8

Speciality polymers/additives (Typical properties)

	Product	T _g °C	Inherent viscosity	Flow rate	T _m °C	T _c °C	Brittleness temperature °C	Vicat softening temperature °C
Copolyester elastomers	Eastman™ AP005	-3	1.05	20g/10 min	207	140	<-75	170
	Eastman™ AP006	-3	1.16	10g/10 min	205	140	<-75	170
	Eastman™ AP007	-3	1.23	4g/10 min	205	140	<-75	170

EASTMAN

Eastman Chemical Company Corporate Headquarters

P.O. Box 431
Kingsport, TN 37662-5280 U.S.A.
Telephone:
U.S.A. and Canada, 800-EASTMAN
(800-327-8626)
Other Locations, (1) 423-229-2000
Fax: (1) 423-229-1193

Eastman Chemical Latin America

9155 South Dadeland Blvd.
Suite 1116
Miami, FL 33156 U.S.A.
Telephone: (1) 305-671-2800
Fax: (1) 305-671-2805

Eastman Chemical B.V.

Fascinatio Boulevard 602-614
2909 VA Capelle aan den IJssel
The Netherlands
Telephone: (31) 10 2402 111
Fax: (31) 10 2402 100

Eastman (Shanghai) Chemical Commercial Company, Ltd. Jingan Branch

1206, CITIC Square
No. 1168 Nanjing Road (W)
Shanghai 200041, P.R. China
Telephone: (86) 21 6120-8700
Fax: (86) 21 5213-5255

Eastman Chemical Japan, Ltd.

AIG Aoyama Building 5F
2-11-16 Minami Aoyama
Minato-ku, Tokyo 107-0062 Japan
Telephone: (81) 3-3475-9510
Fax: (81) 3-3475-9515

Eastman Chemical Asia Pacific Pte. Ltd.

#05-04 Winsland House
3 Killiney Road
Singapore 239519
Telephone: (65) 6831-3100
Fax: (65) 6732-4930

www.eastman.com

Material Safety Data Sheets providing safety precautions, that should be observed when handling and storing Eastman products, are available online or by request. You should obtain and review the available material safety information before handling any of these products. If any materials mentioned are not Eastman products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

Neither Eastman Chemical Company nor its marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment and for the health and safety of your employees and purchasers of your products. NO WARRANTY IS MADE OF THE MERCHANTABILITY OR FITNESS OF ANY PRODUCT, AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Eastman, Endex, Kristalex, Piccolastic, Plastolyn, Regalite and Regalrez are trademarks of Eastman Chemical Company.

© Eastman Chemical Company, 2009.