



Typical Physical Properties PICCOLASTIC hydrocarbon resins

Some products contain physical properties that are not displayed in the columns below. To locate the information needed, please choose the product link below. The properties may be found on the datasheet, SDS or sales specification.

PICCOLASTIC hydrocarbon resins

Products	Ring and Ball Softening Point	Color ^a	Cloud Point ^b			Molecular Weight ^c				Data Sheet	SDS
	ASTM E 28	Gardner	DACP	MMAp	OMS	M _n	M _w	M _w /M _n	M _z		
Piccolastic™ A5	5 °C	2	<-50 °C	-6 °C	140/-5 °C	300	350	1.2	550		
Piccolastic™ A75	74 °C	1	<-50 °C	6 °C	74/70 °C	700	1300	1.9	2250		
Piccolastic™ D125	126 °C	2	-32 °C	13 °C	>180 °C	1300	37400	28.5	179000		

^a - 50% resins solids in toluene

^b - MMAp: cloud point measured in a 1:2 mixture of methylcyclohexane and aniline; DACP: cloud point measured in a 1:1 mixture of xylene and 4-methyl-2-pentanone; OMS: odorless mineral spirits cloud point; For more information see "Hydrocarbon Spectrum", WA-86

^c - Molecular weight measured via Gel Permeation Chromatography (GPC) using polystyrene standards