





Typical Physical Properties Functionalized Polyolefins

Some products contain physical properties that are not displayed in the columns below. To locate the information needed, please choose the product link below. The properties may be found on the datasheet, SDS or sales specification.

Functionalized Polyolefins

Products	Polymer Type	Acid Number (mg KOH/g)	Ring and Ball Softening Point	Penetration Hardness ^a	Viscosity, Brookfield	Molecular Weight ^b	Data Sheet	SDS
				ASTM D 5	@ 190°C (374°F)	M _w		
Eastman™ G-3003	Ma-PP	9	158 DSC T _m , °C	<1 dmm	60,000 cP	52,000		
Eastman™ G-3015	Ma-PP	15	156 DSC T _m , °C	<1 dmm	18,000 cP	47,000		

^a - Needle under 100-g load for 5s @ 25 deg C, tenths of mm

^b - Molecular weight measured via Gel Permeation Chromatography (GPC) using polystyrene standards